

## TAC 2T 315

### POLYMER BASED FLOOR & WALL TILE ADHESIVE

#### FAB ( Features, Benefits & Advantages )

- . For both interior floor and wall applications and for exterior floor applications
- . For installation of vitrified/fully vitrified tiles & glass mosaic tiles
- . Suitable for installations where background and location is more demanding like wet areas, submerged areas etc
- . Can be used to install tiles on to various substrates like : Concrete Masonry, Cement Mortar Beds, Cement Plaster, Existing Vitrified Tile & Ceramic Tile, Brick Masonry, Cement Terrazzo, Existing Natural Stone

#### Coverage

- . Approx. 45 to 50 sq.ft. per 20 Kg pack, using 6mm x 6mm square notched trowel for a bed of 3mm
- . Coverage will depend on the nature and flatness of the surface and the method of application
- . For good coverage, it is must that all surfaces are smooth, plumb, level and free from defects and undulations

#### Working Properties at 27° C

- . TAC 2T 315 Adhesive mixed with Water

Open Time	20 minutes
Pot Life	3 hours
Time to Heavy Traffic	16 - 24 hours

- . Actual performance will depend on installation methods and side conduction

#### Technical data

IS Data		
Property: Testmethod	Requirement	Typical/Values
Tensile Adhesion		
Dry Conditions Annex A (Clause 5.1)	Minimum 1.00 N/mm <sup>2</sup>	1.1-1.2 N/mm <sup>2</sup>
Wet Conditions Annex A (Clause 5.1)	Minimum 1.00 N/mm <sup>2</sup>	1.1-1.2 N/mm <sup>2</sup>
Dry Conditions Annex B (Clause 5.2)	Minimum 1.25 N/mm <sup>2</sup>	1.25-1.40 N/mm <sup>2</sup>
Heat Ageing Annex B (Clause 5.2)	Minimum 1.00 N/mm <sup>2</sup>	1.05-1.15 N/mm <sup>2</sup>
Wet Conditions Annex B (Clause 5.2)	Minimum 1.00 N/mm <sup>2</sup>	1.10-1.20 N/mm <sup>2</sup>
Slipresistance Annex E (Clause 5.5)	≤0.5mm	0.30-0.45mm

#### Standard

TAC 2T 315 complies to IS 15477:2019, CML No. 8400211808 "Type 2T"

Also complies with **EN C1TE** classification



**Packaging**

20 kg

**Colour**

Grey & White

