

GROUT ADMIX

TILE & STONE CARE

FAB (Features, Benefits & Advantages)

- . Good bond strength
- . Water and shock resistant
- . Colour fast
- . Suitable for both Interior, Exterior, Floor&Wall joint width of upto 3mm
- . Easy application and clean up
- . Easy maintenance
- . Non-cracking & non-shrink
- . Designed for grouting glazed wall tiles, porcelain tiles, mosaic, vitrified & fully vitrified tiles, natural and engineered stones



Packaging
200gm

Colour
Multicolor

Working Properties at 27° C

Pot Life	60 minutes
Foot Traffic	24 Hours

Technical data

ISO / EN Data		
Property: Test method	Requirement	Typical Values
Abrasion resistance: ISO 13007-4: Clause 4.4; En 12808-2	≤2000 mm ²	1300 - 1600/mm ²
Flexural strength under standard conditions: ISO 13007-4: Clause 4.1.3; EN 128083	≥2.5 N/mm ²	3.0 - 3.5N/mm ²
Compressive Strength under standard conditions: ISO 13007-4 : Clause	≥15 N/mm ²	820 - 22N/mm ²
Shrinkage: ISO 13007-4: Clause 4.3 : EN 12808 - 4	<3mm / m	2.00 - 2.2mm/m
Water Absorption after 30 Minutes: ISO 13007-4: Clause 4.2;EN 12808 - 5	≤5.0g	2.5 - 3.0 g

The polymer grout conforms to EN 13888.

Coverage

Consumption depends on joint width, size of tiles

Theoretical coverage calculation in kg/m²

$(\text{Tile length} + \text{Tile breadth}) \times \text{Tile thickness} \times \text{Joint width} \times \text{Wet density}^*$

$(\text{Tile length} + \text{Joint width}) \times (\text{Tile breadth} + \text{Joint width})$

All the dimensions are in mm

Standard

- . Complies with TGC 99 En13888.

